

---



---

**AIR DRY SOUND DEADNER NO. 12500**


---



---

<b>Description:</b>	It is a one component air dry high solid sound deadener based on perfect types of resins and pigments.
<b>Advantages:</b>	<ul style="list-style-type: none"> <li>• Very fast drying at ambient temperature.</li> <li>• Very good chemical resistance against lubricant oils, greases, petrol, aqueous solutions and detergents.</li> <li>• Excellent mechanical properties such as adhesion, impact and flexibility.</li> </ul>
<b>Fields of application:</b>	<ul style="list-style-type: none"> <li>• applied on car motors, bottom of chassis ...etc.</li> </ul>
<b>Color</b>	grey / black.
<b>Finish</b>	Matt.
<b>Specific gravity:</b>	1.47 ± 0.1 gm / cm <sup>3</sup>
<b>Solid by volume:</b>	49.5 %.
<b>Solid by weight:</b>	70 %.
<b>Theoretical spreading rate:</b>	2 - 3 m <sup>2</sup> / kg (at D.F.T 200 - 400 micron).
<b>Wet film thickness:</b>	500 microns.
<b>dry film thickness:</b>	250 microns.
<b>Drying time:</b>	<ul style="list-style-type: none"> <li>• Surface: 20 - 30 min. (at 25°C &amp; 60% R.H.).</li> <li>• Complete: 24 hours (at 25°C &amp; 60% R.H.).</li> </ul>
<b>Time to recoat:</b>	<ul style="list-style-type: none"> <li>• Min.: 24 hrs (at 25°C &amp; 60% R.H.).</li> <li>• Max.: no limit.</li> </ul>
<b>Shelf life:</b>	6 months in its closed original cans at good stores in ideal conditions.
<b>Thinner:</b>	No. 10773 or 10151 (PACHIN thinner).
<b>Method of application:</b>	<ul style="list-style-type: none"> <li>• By air spray.</li> <li>• By brush.</li> </ul>
<b>Surface preparation:</b>	<ul style="list-style-type: none"> <li>• It is applied on clean and dry primed surfaces.</li> <li>• Don't apply when the R.H exceeds 85% min.</li> </ul>